



# BROOKLYN




## IPE




## TEAK






## LIGHT GREY



## DARK GREY




## CEDAR



**Cobra Start/End**  
(30 clips + 30 screws)



**Cobra Hybrid 8-18**  
(90 clips + screws)  
1 bag for 4.5 m<sup>2</sup> (138mm)



PROPERTY	TEST METHOD	TEST RESULTS	NOTES / REQUIREMENTS
Composition	-	HDPE = 35% Wood powder = 55% Additives = 10%	-
Density	EN 15534-1	1.240 g/cm <sup>3</sup>	-
Linear mass	EN 15534-1	Width 138 mm : 2.73 Kg/m Width 210 mm : 4.09 Kg/m	-
Deviation from Straightness	EN 15534-1	≤ 1 mm / metre	-
Cupping	EN 15534-1	≤ 0.5 mm	-
Maximum load	EN 15534-1	Width 138 mm : 3953 N Width 210 mm : 5992.75 N	Span : 350 mm F <sub>max</sub> ≥ 3 300 N (EN 15534-4)
Deflection at 500 N	EN 15534-1	Width 138 mm : 1.07 mm Width 210 mm : 1.00 mm	Span : 350 mm ≤ 2.5 mm (EN 15534-4)
Modulus of elasticity	EN 15534-1. Annex A	Width 138 mm : 3512 MPa Width 210 mm : 3231.3 MPa	Span : 350 mm Bending test on finished product at normal condition 20°C and 65% RH
Bending strength	EN 15534-1. Annex A	Width 138 mm : 29.6 MPa Width 210 mm : 25.18 MPa	
Creep behaviour	EN 15534-1	Width 138 mm : Max ΔS = 1.37 mm Mean ΔSr = 1.02 mm Creep factor = 1.27 Creep recovery = 41.5 %	ΔS ≤ 13 mm for individual values ΔSr ≤ 5 mm for arithmetic mean value (EN 15534-4)
		Width 210 mm : Max ΔS = 1.14 mm Mean ΔSr = 0.92 mm Creep factor = 1.74 Creep recovery = 37.5 %	
Resistance to indentation (Brinell Hardness)	EN 15534-1	Brinell hardness: 66.5 MPa Rate of elastic recovery: 65.9 %	Applied load : 2000 N
Resistance to artificial weathering	EN 15534-1	ΔE = 1.14	2000 hours. ISO 4892-2 cycle 1
Swelling and water absorption (28 days)	EN 15534-1 EN 317	Width 138 mm : Swelling: 0.17 % in thickness 0.06 % in width 0.13 % in length Water absorption in weight : 2.69 %	Swelling: ≤ 4 % in thickness ≤ 0.8 % in width ≤ 0.4 % in length (EN 15534-4)  Water absorption in weight ≤ 7 % (EN 15534-4)
		Width 210 mm : Swelling: 0.16 % in thickness 0.03 % in width 0.11 % in length Water absorption in weight : 2.48 %	
Boiling test	EN 15534-1 EN 1087-1	Width 138 mm : Water absorption in weight = 1.67 % Width 210 mm : Water absorption in weight = 1.28 %	Water absorption in weight ≤ 7 % (EN 15534-4)
Falling mass impact resistance	EN 15534-1	No crack	Striker weight : 1000 ± 5 g Falling distance : 700 ± 5 mm No cracks on 10 test specimens. (EN 15534-4)
Surface bond strength	EN 319	3.16 N/mm <sup>2</sup>	-
Abrasion	ASTM D4060-19	53mg	-
Heat reversion	EN 15534-1 EN 479	0.12 %	100°C - 1 hour
Linear thermal expansion coefficient	EN 15534-1	42.1 10 <sup>-6</sup> K <sup>-1</sup>	≤ 50.0 10 <sup>-6</sup> K <sup>-1</sup> (EN 15534-4)
Reaction to fire - Single flame source test	EN 15534-1	Class Efl	FS ≤ 150 mm within 20 s. (EN13501-1)